

A REVIEW STUDY ON USE OF STEEL FIBER AS REINFORCEMENT MATERIAL WITH CONCRETE

Er Gulzar Ahmad¹, Er kshipra Kapoor²

¹M. Tech scholar, Department of civil Engineering, Universal institutions of Engineering and Technology, Lalru, Chandigarh.

²Assistant Prof. & Head, Department of civil Engineering, Universal institutions of Engineering and Technology, Lalru, Chandigarh.

Abstract – Fibers are generally used as resistance of cracking and strengthening of concrete. In this project, I am going to carry out test on steel fiber reinforced concrete to check the influence of fibers on strength of concrete. According to various research papers, it has been found that steel fibers give the maximum strength in comparison to glass and polypropylene fibers. Now a days there exists many reinforcement techniques for improving the strength of those materials which lacks load carrying and less durable capacity. Use of steel fiber to enhance the strength and reduce maintenance is an effective technology established in recent times. Fiber reinforced concrete has been successfully used in slabs on grade, shotcrete, architectural panels, precast products, offshore structures, structures in seismic regions, thin and thick repairs, crash barriers, footings, hydraulic structures and many other applications. The usefulness of fiber reinforced concrete in various Civil Engineering applications is thus indisputable. This review study is a trial of giving some highlights for inclusion of steel fibers especially in terms of using them with new types of concrete.

Keywords — Compressive strength, ductility, flexural strength, Fibre Reinforced Concrete, Steel fiber, Split tensile strength, toughness, workability

1. INTRODUCTION

Application of Fibre Reinforced Concrete (FRC) is continuously growing in various application fields. FRC is widely used in structures. Due to the property that fibre enhances toughness of concrete, FRC is used on large scale for structural purposes. The fibre is described by a convenient parameter called aspect ratio. The aspect ratio of the fiber is the ratio of its length to its diameter. The principle motive behind incorporating fibers into a cement matrix is to increase the toughness and tensile strength and improve the cracking deformation characteristics of the resultant composite. For FRC to be a valuable construction material, it must be able to compete economically with existing reinforcing system. FRC composite properties, such as crack resistance, reinforcement and increase in toughness are dependent on the mechanical properties of the fiber, bonding properties of the fiber and matrix, as well as the quantity and distribution within the matrix of the fibers. It improves fatigue resistance makes crack pattern distributed. By making crack pattern distributed, it is meant that it decreases the crack width. Underground tunneling has a very vast and profound application of SFRC and there is growing interest in SFRC as compared to plain concrete. Rehabilitation of conventional rockbolt and wire mesh support can be very disruptive and expensive. The excavations being shotcrete immediately are increasing. The incorporation of steel fibre reinforcement into the shotcrete is an important factor in this escalating use, since it minimizes labour intensive process of wire mesh installation. Trials and observations suggest that shotcrete can provide effective support in mild rock burst conditions.

1.1 Reinforcement Mechanisms in Fiber Reinforced (FRC)

In the hardened state, when fibers are properly bonded, they interact with the matrix at the level of micro-cracks and effectively bridge these cracks thereby providing stress transfer media that delays their coalescence and unstable growth. If the fiber volume fraction is sufficiently high, this may result in an increase in the tensile strength of the matrix. Indeed, for some high volume fraction fiber composite, a notable increase in the tensile/flexural strength over and above the plain matrix has been reported. Once the tensile capacity of the composite is reached, and coalescence and conversion of micro-cracks to macro-cracks has occurred, fibers, depending on their length and bonding characteristics continue to restrain crack opening and crack growth by effectively bridging across macro-cracks. This post peak macro-crack bridging is the primary reinforcement mechanisms in majority of commercial fiber reinforced concrete composites.

2. LITERATURE REVIEW

To purpose and defend the research work, a number of research papers are analyzed. Following are the excerpts from the different research work performed by number of academicians and researchers.

Milind V mohod (2012) et al in this experimental investigation for M30 grade of concrete to study the compressive strength and tensile strength of steel fibers reinforced concrete containing fibers varied by 0.25%, 0.50%, 0.75% 1% 1.5% and 2% by volume of cement cubes of size 150mmX150mmX150mm to check the compressive

Publication History

Manuscript Received : 14 June 2016
Manuscript Accepted : 20 June 2016
Revision Received : 25 June 2016
Manuscript Published : 30 June 2016

strength and beams of size 500mmX100mmX100mm for checking flexural strength were casted. All the specimens were cured for the period OF 3, 7 and 28 days before crushing the result of fibers reinforced concrete 3 days, 7 days, and 28 days curing with varied percentage of fiber were studied and it has been found that there is significant strength improvement in steel fiber reinforced concrete. The optimum fiber content while studying the compressive strength of cube is found to be 10% and 0.75% for flexural strength of the beam.

Also it has been observed that with the increase in fiber content up to the optimum value increase the strength of concrete.

Vikrant Vairagade et al (2012) presented the applicability of previously published relation among compressive strength tensile strength flexural strength of normal concrete to steel fibers reinforced concrete was evaluated and mechanical properties of steel reinforced concrete were analyzed in this experimental study cement sand coarse aggregate water and steel fibers were used for compressive strength test both cube specimens of dimensions 150mm × 150mm × 150mm and cylindrical specimen of length 200mm and diameter 100mm were cast for M20 grade filled with 0% and 0.5% fibers after 24 hours the specimens were to curing tank where in they were allowed cure for 7 days and 28 days. Finally result of compressive strength for M20 grade of concrete on cube and cylinder specimens with 0% and 0.5% steel fibers for aspect ratio 50 and 53.85 is it observed that for addition of 0.5% fibers shows slightly more compressive strength than normal concrete.

Prof. Ram Meghe et al (2014) presented the experimental study of the steel fibers reinforced self compacting concrete by addition of different content of steel fibers the result showed that the split tensile strength found to be increased with the addition of steel fibers and the optimum fiber content for increasing the split tensile strength was found to be 1.75% it was been observed that the steel fibers are used in the concrete to give the maximum strength as compared to other fibers such as glass fibers polypropylene fibers. The compressive strength and the flexural strength observed to be increased as the percentage of steel fibers are increased in the steel fibers reinforced concrete.

Elson John et al (2014) in this study it was observed that the physical properties of the concrete after adding the different volume fractions of fibers are used in the concrete. In the mix design is carried out as per 10262:2009 the proportioning is carried out to achieve strength at specified age, workability of fresh and durability requirements. The materials selected for this experimental study includes normal natural coarse aggregate, manufactured sand as fine aggregate, cement ,Superplasticizer both end hooked steel fibers and portable drinking water.

The physical and chemical properties of each ingredient has considerable role in the desirable properties of concrete like strength and workability finally the test result of compressive strength split tensile strength and flexural strength it can be seen that in the presence of steel fiber there is an increase in compressive strength split tensile strength and flexural strength the small in fiber specimen compared to the non fibers specimens.

Ahsana Fathima et al (2014) presented the experimental study on the effect of steel fibers and polypropylene fibers on the mechanical properties of concrete, experimental program consisted of compressive strength test, split tensile strength test and flexural strength test on steel fiber reinforced concrete polypropylene fiber reinforced concrete three types of fibers used of length 30mm crimped steel fibers of length 25mm and endure 600 polypropylene of length 50mm with aspect ratio 50. The main aim of this experiment is to study the strength properties of steel fibers and polypropylene. Fibers reinforced concrete of M30 grade with 0%, 0.25%, 0.5% and 0.75% by volume of concrete.

V. T. Babar et al investigated the shear strength and ductility of fiber reinforced concrete beams by using hooked steel fiber without stirrups. In this investigation, the test beam specimens of 125 mm in width, 250 mm in depth, and 1150 mm in length are cast and steel fibers are varied from 0.5 % up to 2 % volume fraction The longitudinal steel is kept constant, while shear span-to-depth ratio (a/d) is varied in the range 1, 1.25, and 1.5. All the beam specimens are tested under two-point loading up to failure, and failure load, first crack load, and central deflection are recorded concisely and precisely. The test specimens were cast using cement, fine aggregate, coarse aggregate, water, and Hooked steel fibers. The materials, in general, confirmed to the specifications laid down in the relevant Indian Standard codes. For grading of fine and coarse aggregate, sieve analysis was carried out. Ordinary portland cement of 53-grade confirming to IS 12269:1987 was used throughout the experimental work. The maximum size of coarse aggregate used was 20 mm along with 12.5 mm of same parent rock in 60-40 % fraction. Locally available Krishna river sand was used as fine aggregate. The specific gravity of sand was 2.85 and fineness modulus was 2.7. Hooked end steel fibers of length 60 mm and diameter 0.75 mm were used throughout the experimental work. Reinforcing steel of grade Fe 500 was used as tensile reinforcement.

Nitin Kumar et al (2015) presented the use of steel fibers as reinforcement material with concrete. In this study, the mixing of various materials weather chemicals natural or official for improving the strength and durability of parent substance. Critical investigation for M 40 grade of concrete having mix proportion 1:4:3 with water cement ratio 0.35 to study the compressive strength flexural strength, split tensile strength of steel fibers reinforced concrete containing fibers of 0%, 1%, 2% and 3% volume fraction of hooks the result shown that steel fiber reinforced concrete increase strength toughness ductility and flexural strength of concrete.

CONCLUSIONS

The study on the introduction of effect of steel fibers can be still promising as steel fiber reinforced concrete is used for sustainable and long-lasting concrete structures. Steel fibers are widely used as a fiber reinforced concrete all over the world. Lot of research work had been done on steel fiber reinforced concrete and lot of researchers work prominently over it. This review study tried to focus on the most significant effects of addition of steel fibers to the concrete mixes. The steel fibers are mostly used fiber for fiber reinforced concrete out of available fibers in market. According to many researchers, the addition of steel fiber

into concrete creates low workable or inadequate workability to the concrete, therefore to solve this problem of Superplasticizer without affecting other properties of concrete may introduce.

ACKNOWLEDGEMENT

The review study described in this paper was a part of M-Tech research work at Universal institutions of Engineering and Technology, Lalru, Chandigarh.

REFERENCES

- [1] Milind V. Mohod, “ Performance of Steel Fiber Reinforced Concrete” IICS ISSN: 2278-4721, Vol. 1, Issue 12 (December 2012), PP 01-04
- [2] AHSANA FATHIMA K M & SHIBI VARGHESE, “BEHAVIOURAL STUDY OF STEEL FIBER AND POLYPROPYLENE FIBER REINFORCED CONCRETE” ISSN(E): 2321-8843; ISSN(P): 2347-4599, Vol. 2, Issue 10, Oct 2014, 17-24
- [3] N. Ganesan, P.V. Indira and Ruby Abraham, “STEEL FIBRE REINFORCED HIGH PERFORMANCE CONCRETE BEAM-COLUMN JOINTS SUBJECTED TO CYCLIC LOADING”
- [4] N. Janesan, P. V. Indira and S. Rajendra Prasad, 2010: “Structural behaviour of steel fibre reinforced concrete wall panels in two-way is plane action.” Indian concrete journal.
- [5] Rui D. Neves and Joao C. O. Fernandes de Almeida, 2005. “Compressive behaviour of steel fibre reinforced concrete”, structural concrete. 2005-06. No. 1.
- [6] Jiuru, T., Chaobin, H., Kaijian, Y. and Yongcheng, Y. (1992). “Seismic Behaviour and Shear Strength of Framed Joint Using Steel-Fiber Reinforced Concrete”, Journal of Structural Engineering, ASCE, Vol. 118, No. 2, pp. 341–358.
- [7] Kumar, V., Nautiyalil, B.D. and Kumar, S. (1991). “A Study of Exterior Beam-Column Joints”, The Indian Concrete Journal, Vol. 65, No. 1, pp. 39–43.
- [8] Oh, B.H. (1992). “Flexural Analysis of Reinforced Concrete Beams Containing Steel Fibres”, Journal of Structural Engineering, ASCE, Vol. 118, No. 10, pp. 2821–2836.
- [9] Shamim, M. and Kumar, V. (1999). “Behaviour of Reinforced Concrete Beam-Column Joint—A Review”, Journal of Structural Engineering, ASCE, Vol. 26, No. 3, pp. 207–213.
- [10] Shannag, M.J., Abu-Dyya, N. and Abu-Farsakh, G. (2005). “Lateral Load Response of High Performance Fiber Reinforced Concrete Beam-Column Joints”, Construction and Building Materials.
- [11] Dwarakanath HV, Nagaraj TS.(1991),” Comparative Study of Predictions of Flexural Strength of Steel Fiber Concrete”, ACI Materials Journal, Vol 88, NO. 73, pp.49-58.
- [12] James J, Beaudoin (1990)“Handbook of Fiber Reinforced Concrete; principles, properties, Development and Applications”, Noyes Publications, New Jersey, United State of America.,pp.57-63
- [13] Patton ME, Whittaker WL.(1983) “Effects of fiber Content and Damaging Load on Steel Fiber Reinforced Concrete Stiffness”, ACI Journal, Vol .80, No.1